

"Express Mail" mailing label number
EL 500 982 789 US

Date of Deposit December 17, 2001.

FORM PTO-1390 (REV. 5-93)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE	CASE NO. 5404/15
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371		U.S. APPLICATION NO. 10/018905 (37 CFR 1.5)	
INTERNATIONAL APPLICATION NO. PCT/JP00/04126	INTERNATIONAL FILING DATE June 23, 2000	PRIORITY DATE CLAIMED	
TITLE OF INVENTION REGENERATED COLLAGEN FIBER REDUCED IN ODOR AND IMPROVED IN SUITABILITY FOR SETTING, PROCESS FOR PRODUCING THE SAME, AND METHOD OF SETTING			
APPLICANT(S) FOR DO/EO/US Masahiro Ueda et al.			
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:			
<p>1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371</p> <p>2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371</p> <p>3. <input checked="" type="checkbox"/> This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).</p> <p>4. <input type="checkbox"/> A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.</p> <p>5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 U.S.C. 371(c)(2)).</p> <p style="margin-left: 40px;">a. <input checked="" type="checkbox"/> is transmitted herewith (required only if not transmitted by the International Bureau).</p> <p style="margin-left: 40px;">b. <input type="checkbox"/> has been transmitted by the International Bureau.</p> <p style="margin-left: 40px;">c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US).</p> <p>6. <input checked="" type="checkbox"/> A translation of the International Application into English (35 U.S.C. 371(c)(2)).</p> <p>7. <input checked="" type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)).</p> <p style="margin-left: 40px;">a. <input type="checkbox"/> are transmitted herewith (required only if not transmitted by the International Bureau).</p> <p style="margin-left: 40px;">b. <input type="checkbox"/> have been transmitted by the International Bureau.</p> <p style="margin-left: 40px;">c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired.</p> <p style="margin-left: 40px;">d. <input checked="" type="checkbox"/> have not been made and will not be made.</p> <p>8. <input type="checkbox"/> A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).</p> <p>9. <input checked="" type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).</p> <p>10. <input type="checkbox"/> A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)) and/or amendments under Article 34.</p>			
Items 11. to 16. Below concern other document(s) or information included:			
11. <input type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98.			
12. <input checked="" type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.			
13. <input type="checkbox"/> A FIRST preliminary amendment.			
<input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment.			
14. <input type="checkbox"/> A substitute specification.			
15. <input checked="" type="checkbox"/> A change of power of attorney and/or address letter.			
16. <input type="checkbox"/> Other items or information:			

U.S. APPLICATION NO. 10/018905 <small>(If known, see 37 CFR 1.50)</small>		INTERNATIONAL APPLICATION NO. PCT/JP00/04126		CASE NO. 5404/15	
17. <input checked="" type="checkbox"/> The following fees are submitted: Basic National Fee (37 CFR 1.492(a)(1)-(5)): Search Report has been prepared by the EPO or JPO\$890.00 International preliminary examination fee paid to USPTO (37 CFR 1.492(a)(1))\$710.00 No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee paid to USPTO (37 CFR 1.492(a)(2))\$740.00 Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.492(a)(3)) paid to USPTO\$1,040.00 International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(1)-(4)\$100.00 <div style="text-align: center; font-weight: bold; margin-top: 10px;">ENTER APPROPRIATE BASIC FEE AMOUNT</div>				CALCULATIONS PTO USE ONLY	
				\$890	
Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)).					
Claims	Number Filed	Number Extra	Rate		
Total Claims	18- 20 =	0	x \$ 18.00		
Independent Claims	1- 3 =	0	x \$ 84.00		
Multiple dependent claim(s) if Applicable)			0	+ \$280.00	\$280.00
TOTAL OF ABOVE CALCULATIONS =				\$1170	
Reduction by 1/2 for filing by small entity, if applicable. Verified Small Entity statement must also be filed. (Note 37 CFR 1.9, 1.27, 1.28)					
SUBTOTAL =				\$1170	
Surcharge of \$130.00 for furnishing the English translation later than the <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				\$	
TOTAL NATIONAL FEE=				\$1170	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31), \$40.00 per property +				40.00	
TOTAL FEES ENCLOSED=				\$1210	
				Amount to be refunded	\$
				charged	\$
a. <input checked="" type="checkbox"/> A check in the amount of \$1210 to cover the above fees is enclosed. b. <input type="checkbox"/> Please charge my Deposit Account No. 23-1925 in the amount of \$ to cover the above fees. A duplicate copy of this sheet is enclosed. c. <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 23-1925. A duplicate copy of this sheet is enclosed.					
NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.					
Send All Correspondence to: Brinks Hofer Gilson & Lione P.O. Box 10395 Chicago, IL 60610			<div style="font-family: cursive; font-size: 1.5em; margin-bottom: 10px;">Richard G. Lione</div> Signature Richard G. Lione Name 19,795 Registration Number		

DESCRIPTION

REGENERATED COLLAGEN FIBER REDUCED IN ODOR AND
IMPROVED IN SUITABILITY FOR SETTING, PROCESS FOR PRODUCING
5 THE SAME, AND METHOD OF SETTING

TECHNICAL FIELD

The present invention relates to regenerated collagen fibers improved in suitability for setting. More specifically, the present
10 invention relates to regenerated collagen fibers which have light color and excellent touch in wet conditions, which can be formed into a desirable shape easily with the shape being maintained properly and whose foul odor generated in thermal treatment is inhibited. The present invention also relates to a process for preparing the same.
15 Such regenerated collagen fibers can be suitably used for curling hair ornaments such as wigs, hairpieces and doll hair or for shaping (setting) textile goods comprising woven fabrics or non-woven fabrics.

BACKGROUND ART

20 In order to produce regenerated collagen fibers, a process is adopted in general which comprises treating skin or bone of animals as a raw material with alkali or enzyme, decomposing and removing telopeptide in collagen to make it water-soluble, and spinning the same. Herein, the obtained regenerated collagen fibers are also soluble in water.
25 In addition, when the regenerated collagen fibers contain water, shrinking starts at about 30° to 40°C, meaning that water resistance thereof is extremely inferior.

To make regenerated collagen fibers water-resistant with maintaining its light color, there are processes for treating collagen fibers with metallic salt such as aluminum salt or zirconium salt as disclosed in Japanese Unexamined Patent Publication No. 50370/1992, 5 Japanese Unexamined Patent Publication No. 173161/1994 and Japanese Unexamined Patent Publication No. 308221/1992, and a process for treating collagen fibers with an epoxy compound as disclosed in Japanese Unexamined Patent Publication No. 352804/1992. As a process for shaping regenerated collagen fibers, a process disclosed in 10 Japanese Unexamined Patent Publication No. 333660/1992 or Japanese Unexamined Patent Publication No. 250081/1997 which comprises moisturizing fibers in warm water or an aqueous solution containing monovalent or divalent cationic hydrosulfate, and heat-treating the fibers is known. However, when the regenerated collagen 15 fibers which are made water-resistant by the treatment with metallic salt such as aluminum salt or zirconium salt are shaped according to the above method, shape keeping ability (set property) thereof is extremely low though certain shape can be given to the fibers. Furthermore, the given shape is lost immediately when water washing (including shampoo 20 washing) and drying are repeated. Thus, it was difficult to use these fibers for hair products such as wigs, hairpieces and doll hair.

Though light color fibers are also obtained by using formaldehyde, the obtained fibers were not satisfactory in shaping property either. Additionally, in case of using a multivalent alcohol, i.e., 25 glycidyl ether which is regarded as the most preferable compound among epoxy compounds described in Japanese Unexamined Patent Publication No. 352804/1992, fibers became brittle and hard, and

strength thereof was remarkably lost, causing problems during production process of hair ornament, for example, hair implant or sewing machine operation. Furthermore, the fibers were not satisfactory in shaping property either.

5 An object of the present invention is to provide regenerated collagen fibers which have light color and excellent touch in wet conditions, which can be formed into a desirable shape easily and whose setting can be carried out with maintaining the shape properly.

10 DISCLOSURE OF INVENTION

 In view of the current conditions mentioned above, the present invention has been completed based on the findings that it is possible to obtain regenerated collagen fibers which have natural light color of collagen, improved hardness when the fibers are wet, and
15 excellent touch in wet conditions by combining two kinds of treatment, namely, treatment by a monofunctional epoxy compound and treatment by an aluminum salt.

 The present invention relates to regenerated collagen fibers which are obtained by treating collagen with a monofunctional epoxy
20 compound and an aluminum salt.

 The present invention also relates to a process for preparing regenerated collagen fibers which comprises treating collagen with a monofunctional epoxy compound and then treating the same in such a way that 2 to 40 % by weight of an aluminum salt converted to an
25 aluminum oxide (Al_2O_3) basis is contained to said collagen.

 The present invention also relates to a process for setting regenerated collagen fibers which comprises thermally setting the

regenerated collagen fibers by means of hot water treatment at 20° to 100°C and heat drying treatment at 60° to 220°C.

BRIEF DESCRIPTION OF DRAWINGS

5 Fig. 1 is a chart obtained by measurement of gas generated from regenerated collagen fibers prepared in Example 6 by using a gas chromatograph mass spectrometer.

 Fig. 2 is a chart obtained by measurement of gas generated from regenerated collagen fibers prepared in Example 7 by using a gas
10 chromatograph mass spectrometer.

BEST MODE FOR CARRYING OUT THE INVENTION

 The regenerated collagen fibers of the present invention are obtained by treating collagen with a monofunctional epoxy compound and an aluminum salt. It is preferable that the regenerated collagen
15 fibers of the present invention are obtained by treatment with a monofunctional epoxy compound and an aluminum salt after oxidizing methionine groups. Alternatively, part or all of the methionine groups in the collagen fibers may be present in the form of sulfoxidized
20 methionine group or sulfonated methionine group.

 It is preferable to use split hide as a raw material of collagen in the present invention. Such split hide is obtained from fresh split hide or salted rawhide of slaughtered animals such as cows. Split hide comprises insoluble collagen fibers for the most part and used after
25 cleaning reticulated flesh or removing salt added to prevent decay and deterioration.

 The insoluble collagen fibers contain impurities such as lipid

including glyceride, phospholipid or free fatty acid, and protein other than collagen such as glycoprotein or albumin. These impurities have great influence on spinning stability in forming fiber, qualities such as gloss, strength and elongation, and smell in the process of fiber spinning.

5 Therefore, it is preferable to remove the above impurities previously by carrying out conventional leather treatment such as acid or alkali treatment, enzyme treatment or solvent treatment after disassembling collagen fibers by soaking the collagen fibers, for example, in lime to hydrolyze lipid in the insoluble collagen fibers.

10 The thus-treated insoluble collagen fibers are then subjected to solubilization treatment in order to cut the crosslinked peptides. As the process for solubilization treatment, generally known alkali solubilization processes or enzyme solubilization processes can be adopted.

15 In case of applying the alkali solubilization process, neutralization is preferably carried out by acid such as hydrochloric acid. Alternatively, a process disclosed in Japanese Examined Patent Publication No. 15033/1971 may be used as an improved method of conventionally known alkali solubilization processes.

20 The above enzyme solubilization process has an advantage that regenerated collagen having uniform molecular weight can be obtained, and can be suitably used for the present invention. As the enzyme solubilization process, it is possible to adopt processes described in Japanese Examined Patent Publication No. 25829/1968
25 and Japanese Examined Patent Publication No. 27513/1968. Furthermore, both of the above alkali solubilization process and the enzyme solubilization process may be employed together.

Collagen treated with the above solubilization process is preferably subjected to further treatment such as pH adjustment, salting out, water washing or solvent treatment, since regenerated collagen having excellent qualities can be obtained if such treatment is carried
5 out.

The obtained solubilizable collagen is dissolved by using an acidic solution whose pH is adjusted to pH 2 to pH 4.5 with an acid such as hydrochloric acid, acetic acid or lactic acid to obtain a concentrate
10 solution having a given concentration of, for example, about 1 to 15 % by weight, preferably about 2 to 10 %. If necessary, the obtained collagen aqueous solution may be subjected to defoaming with stirring under reduced pressure or filtration in order to remove water-insoluble minute contaminant. If necessary, a suitable amount of additives such as a stabilizer and a water-soluble polymer compound may be added to the
15 solubilizable collagen solution to be obtained for the purpose of increasing mechanical strength, enhancement of water resistance and heat resistance, development of gloss, improvement of fiber spinning properties, coloring prevention, corrosion proof, and the like.

The solubilizable collagen solution is discharged, for example,
20 from a spinning nozzle or a slit and immersed into an inorganic salt aqueous solution to prepare regenerated collagen fibers. An aqueous solution of water-soluble inorganic salts such as sodium sulfate, sodium chloride and ammonium sulfate is used as the inorganic salt aqueous solution. Usually, concentration of these inorganic salts is adjusted to
25 10 to 40 % by weight. The pH of the inorganic salt solution is generally adjusted to pH 2 to pH 13, preferably pH 4 to pH 12 by adding, for example, a metallic salt such as sodium borate or sodium acetate,

hydrochloric acid, boric acid, acetic acid, sodium hydroxide, and the like. In the case where the pH is less than 2 and the case where the pH is more than 13, there is a tendency that peptide bond in collagen is easily hydrolyzed and it becomes difficult to obtain the aimed fibers. The
5 temperature of the inorganic salt solution is not particularly limited, but preferably at most 35°C in general. When the temperature is higher than 35°C, solubilizable collagen tends to be denatured, or strength of fibers to be obtained is lowered, making stable fiber spinning difficult. The lowest temperature is not particularly limited and suitably adjusted
10 in accordance with the solubility of inorganic salt.

A suitable amount of additives such as a stabilizer and a water-soluble polymer compound may be added to the solubilizable collagen solution obtained in the above manner, if necessary, for the purpose of increasing mechanical strength, enhancement of water
15 resistance and heat resistance, development of gloss, improvement of fiber spinning properties, coloring prevention, corrosion proof, and the like.

In the present invention, the above regenerated collagen fibers are treated with a monofunctional epoxy compound or by
20 immersion to solution thereof.

Concrete examples of the monofunctional epoxy compound are olefin oxides such as ethylene oxide, propylene oxide, butylene oxide, isobutylene oxide, octene oxide, styrene oxide, methylstyrene oxide, epichlorohydrin, epibromohydrin or glycidol, glycidyl ethers such as
25 glycidyl methyl ether, butyl glycidyl ether, octyl glycidyl ether, nonyl glycidyl ether, undecyl glycidyl ether, tridecyl glycidyl ether, pentadecyl glycidyl ether, 2-ethylhexyl glycidyl ether, allyl glycidyl ether, phenyl

glycidyl ether, cresyl glycidyl ether, t-butylphenyl glycidyl ether, dibromophenyl glycidyl ether, benzyl glycidyl ether, polyethyleneoxide glycidyl ether, glycidyl esters such as glycidyl formate, glycidyl acetate, glycidyl acrylate, glycidyl methacrylate or glycidyl benzoate, glycidyl amides and the like. However, the present invention is not limited to these examples.

Among monofunctional epoxy compounds, it is preferable to use the monofunctional epoxy compound represented by the following formula (1) to lower water adsorption of the regenerated collagen fibers:



wherein R indicates a substituent group represented by R_1- , $\text{R}_2-\text{O}-\text{CH}_2-$ or $\text{R}_2-\text{COO}-\text{CH}_2-$, R_1 in the substituent group indicates a hydrocarbon group having at least 2 carbon atoms or CH_2Cl and R_2 indicates a hydrocarbon group having at least 4 carbon atoms.

Examples of the compound represented by the above formula (1) are butylene oxide, octene oxide, styrene oxide, methylstyrene oxide, epichlorohydrin, butyl glycidyl ether, octyl glycidyl ether, nonyl glycidyl ether, undecyl glycidyl ether, tridecyl glycidyl ether, pentadecyl glycidyl ether, 2-ethylhexyl glycidyl ether, phenyl glycidyl ether, cresyl glycidyl ether, t-butylphenyl glycidyl ether, benzyl glycidyl ether, glycidyl benzoate and the like.

In particular, monofunctional epoxy compounds whose R_1 in the above formula is hydrocarbon group having 2 to 6 carbon atoms or CH_2Cl , such as butylene oxide, octene oxide, styrene oxide or

epichlorohydrin, or monofunctional epoxy compounds whose R_2 in the above formula is hydrocarbon group having 4 to 6 carbon atoms, such as butyl glycidyl ether, phenyl glycidyl ether or glycidyl benzoate are preferably used from the viewpoints that treatment can be carried out
5 faster due to high reactivity and that treatment in water is relatively easy.

The amount of the monofunctional epoxy compound is 0.1 to 500 equivalent, preferably 0.5 to 100 equivalent, more preferably 1 to 50 equivalent based on the amount of amino group which can react with
10 the monofunctional epoxy compound in the regenerated collagen fibers measured according to the method of amino acid analysis. When the amount of the monofunctional epoxy compound is less than 0.1 equivalent, insolubilization effect of regenerated collagen fibers against water is insufficient. On the other hand, the amount of more than 500
15 equivalent is unfavorable from the viewpoint of industrial handling or from an environmental point of view though insolubilization effect is satisfactory.

The monofunctional epoxy compound is used as it is or after dissolving the same into various solvents. Examples of the solvent are
20 water, alcohols such as methyl alcohol, ethyl alcohol or isopropanol, ethers such as tetrahydrofuran and dioxane, organic halogenated organic solvents such as dichloromethane, chloroform and carbon tetrachloride, neutral organic solvents such as dimethylformamide (DMF) and dimethylsulfoxide (DMSO), and the like. A mixed solvent thereof may
25 also be used. When water is used as the solvent, an aqueous solution of inorganic salt such as sodium sulfate, sodium chloride or ammonium sulfate may be used if necessary. Usually, the concentration of these

inorganic salts is adjusted to 10 to 40 % by weight. The pH of the aqueous solution may be adjusted by adding metallic salts such as sodium borate or sodium acetate, hydrochloric acid, boric acid, acetic acid and sodium hydroxide. In this case, the pH is preferably at least 6,
5 more preferably at least 8. When the pH is less than 6, the reaction between epoxy group in the monofunctional epoxy compound and amino group in collagen slows down, making insolubilization against water insufficient. As pH tends to decrease with time, a buffer may be used if necessary.

10 The temperature for treating regenerated collagen fibers by using an epoxy compound is preferably at most 50°C. When the treatment temperature is higher than 50°C, regenerated collagen fibers tend to be denatured and strength of the fibers to be obtained is lowered, making stable fiber spinning difficult.

15 In addition, various additives such as catalysts and reaction auxiliaries may also be used. Examples of the catalyst are amines and imidazoles. Concretely, examples of the amines include tertiary amines such as triethyl diamine, tetramethyl guanidine, triethanol amine, N,N'-dimethylpiperazine, benzyldimethyl amine, dimethylaminomethyl
20 phenol and 2,4,6-tris(dimethylaminomethyl)phenol, secondary amines such as piperazine and morpholine, quaternary ammonium salts such as tetramethyl ammonium salt, tetraethyl ammonium salt and benzyltriethyl ammonium salt, and the like. Examples of the imidazoles include 2-methylimidazol, 2-ethylimidazole, 2-
25 isopropylimidazol, 1-cyanoethyl-2-methylimidazol, 1-cyanoethyl-2-ethylimidazole, 1-cyanoethyl-2-isopropylimidazol, 2-ethyl-4-methylimidazol, and the like. Examples of the reaction auxiliary are

salicylic acid or metallic salt of salicylic acid; thiocyanic acid salts such as thiocyanic acid and ammonium thiocyanate; tetramethylthiramdisulfide; thiourea; and the like.


In the present invention, the regenerated collagen fiber is
5 subjected to water washing if necessary. Water washing has an advantage of removing inorganic salt which was mixed to the fibers during the fiber spinning process.

The above regenerated collagen fibers are then immersed into an aluminum salt aqueous solution in the present invention.
10 According to this treatment, hardness can be imparted to regenerated collagen fibers even in wet conditions, wet touch of fibers is improved and shaping such as curl setting becomes excellent. Alternatively, a process disclosed in Japanese Unexamined Patent Publication No. 173161/1994 may be adopted as an improved method of conventionally
15 known aluminum salt treatment.

The treatment is carried out so that fibers after treatment contain 2 to 40 % by weight, preferably 2 to 20 % by weight, more preferably 5 to 20 % by weight of an aluminum salt converted to an aluminum oxide (Al_2O_3) basis. When the amount is less than 2 % by
20 weight, wet touch of fibers becomes poor and shaping such as curl setting are weak. When the amount is more than 40 % by weight, fibers after treatment are hardened, making it impossible to achieve favorable touch.

The kind of aluminum salt used herein is not particularly
25 limited. Examples thereof are aluminum sulfate, aluminum chloride, basic aluminum chloride, basic aluminum sulfate and the like. Basic aluminum chloride and basic aluminum sulfate are represented by the

following formula (II) and (III), respectively:



wherein n is 0.5 to 2.5.

These aluminum salts may be used alone or in combination of two or more. The concentration of the aluminum salt in aqueous solution thereof is preferably 0.3 to 5 % by weight converted to an aluminum oxide (Al_2O_3) basis. When the concentration is less than 0.3 % by weight, regenerated collagen fibers tend to have a small aluminum content, wet touch of fibers becomes inferior and shaping such as curl setting becomes weak. When the concentration is more than 5 % by weight, fibers after treatment are hardened, making it impossible to achieve favorable touch.

The pH of the aluminum salt aqueous solution is normally adjusted to pH 2.5 to pH 6.5, preferably pH 2.5 to pH 5.5 by using, for example, hydrochloric acid, sulfuric acid, acetic acid, sodium hydroxide, sodium carbonate or the like. When the pH is less than 2.5, there is a tendency that collagen structure is destroyed and denatured. When the pH is more than 6.5, aluminum salt precipitates and is hardly immersed into fibers. The pH can be adjusted by adding, for example, sodium hydroxide or sodium carbonate to fibers. It is preferable to immerse an aluminum salt solution into regenerated collagen fibers with adjusting the pH to 2.2 to 5.0 at first, and then complete the immersion with adjusting the pH to 3.5 to 6.5. When an aluminum salt having

high basicity is used, it may be sufficient to carry out only the first pH adjustment of 2.5 to 6.5. The temperature of the aluminum salt solution is not particularly limited, but preferably at most 50°C. When the temperature of the solution is higher than 50°C, regenerated collagen fibers tend to be denatured.

The time to immerse an aluminum salt aqueous solution into regenerated collagen fibers is at least 10 minutes, preferably 1 to 25 hours. When the immersion time is shorter than 10 minutes, reaction of aluminum salt is difficult to proceed and improvement of wet touch of fibers is insufficient. Though there is no particular upper limit for the immersion time, reaction of aluminum salt proceeds sufficiently and wet touch of fibers becomes excellent within 25 hours.

In order to avoid uneven concentration by rapid absorption of aluminum salt into regenerated collagen fibers, inorganic salts such as sodium chloride, sodium sulfate and potassium chloride may be suitably added to the above aluminum salt aqueous solution in a concentration of 1 to 20 % by weight. In order to improve stability of aluminum salt in water, an organic salt such as sodium formate or sodium citrate may be suitably added to the above aluminum salt aqueous solution in a concentration of 0.1 to 5 % by weight, preferably 0.5 to 2 % by weight.

The regenerated collagen fibers treated with aluminum salt are then subjected to washing in water, oiling and drying. Washing is carried out, for example, in water for about 10 minutes to 4 hours. As the oil solution used for oiling, it is possible to use an oil solution comprising an emulsion such as silicones modified with amino group, silicones modified with epoxy group, silicones modified with polyether,

and PLURONIC polyether antistatic agent. Drying is carried out at the temperature of preferably at most 100°C, more preferably at most 75°C under gravity of 0.01 to 0.25 g, preferably 0.02 to 0.15 g per 1 dtex.

Water washing is carried out at this stage in order to prevent
5 oil precipitation due to salt, or to prevent generation of break in regenerated collagen fibers caused by the salt precipitated from the regenerated collagen fibers during the drying step in a dryer. In addition, water washing can prevent lowering of heat transfer coefficient caused by the salt scattered and adhered to the heat exchanger in the
10 dryer. When oiling is carried out, there are effects on prevention of sticking of fibers and improvement of surface properties thereof in dry conditions.

Meanwhile, fibers treated with a monofunctional epoxy group have problems of generating foul odor when heat is applied to the fibers during the drying process or the like, such foul odor being intensified
15 when fibers as hair materials are exposed to higher temperature by using a dryer or hair iron. The reason of this foul odor is the sulfur-containing compound generated when the methionine group unstabilized by the reaction of the monofunctional epoxy compound with sulfur atom in the methionine group is thermally decomposed
20 during heat treatment including drying process or the like. It is possible to inhibit this foul odor by using, in the reaction with a monofunctional epoxy group, regenerated collagen fibers whose methionine group is changed to, for example, sulfoxidized methionine
25 group or sulfonated methionine group by oxidation.

In particular, foul odor may be intensified when a monofunctional epoxy group and a metallic salt such as an aluminum

salt are used together as in the present invention since the metallic salt acts as a catalyst for the thermal decomposition. In such cases, it is very effective to use, in the reaction with a monofunctional epoxy compound, regenerated collagen fibers whose methionine group is
5 oxidized and changed to sulfoxidized methionine group or sulfonated methionine group.

As the process for oxidizing methionine group in collagen, there is a process for treating collagen with an oxidant. The treatment with the oxidant may be carried out at any stage as long as it precedes
10 the treatment with the monofunctional epoxy group. In case of treating a solid material such as split hide or regenerated collagen fibers after fiber spinning, the treatment may be carried out by immersing the solid material in an oxidant or solution thereof. In case of treating a
15 solubilized collagen aqueous solution, the treatment may be carried out by adding an oxidant or solution thereof to the collagen solution and mixing the solution sufficiently.

Examples of the oxidant are peroxides such as peracetic acid, perbenzoic acid, benzoyl peroxide, perphthalic acid, m-chloro perbenzoic acid, t-butyl hydroperoxide, periodic acid, sodium periodate
20 and hydrogen peroxide, nitrogen oxides such as nitrogen dioxide, nitric acid, dinitrogen tetroxide and pyridine-N-oxide, metal oxides such as potassium permanganate, absolute chromic acid, sodium bichromate and manganese dioxide, halogens such as chlorine, bromine and iodine, halogenating agents such as N-bromosuccinimide, N-chlorosuccinimide
25 and sodium hypochlorite, and the like. Among these, hydrogen peroxide is preferably used since by-products do not remain in the regenerated collagen fibers and handling of hydrogen peroxide is easy.

The oxidant is used as it is or by dissolving the same into various solvents. Examples of the solvent are water, alcohols such as methyl alcohol, ethyl alcohol or isopropanol, ethers such as tetrahydrofran and dioxane, organic halogen solvents such as dichloromethane, chloroform and carbon tetrachloride, neutral organic solvents such as DMF and DMSO, and the like. A mixed solvent thereof may also be used. When water is used as the solvent, an aqueous solution of inorganic salt such as sodiumsulfate, sodium chloride or ammonium sulfate may be used if necessary. Usually, the concentration of such inorganic salt is adjusted to 10 to 40 % by weight.

As to the amount of the oxidant, it is most preferable from an industrial point of view that all of the oxidant is used for the reaction. The amount of the oxidant in this case is 1.0 equivalent based on the amount of methionine group in the regenerated collagen fibers (for example, according to amino acid analysis, the number of methionine groups present in regenerated collagen fibers derived from cow skin is 6 per 1,000 amino acid groups constituting collagen). However, since some portions of the oxidant are not involved in the actual reaction, the oxidant should be used in an amount of at least 1.0 equivalent.

In case where a solid material such as split hide or regenerated collagen fibers after fiber spinning is immersed in an oxidant solution, it is necessary to use the oxidant solution in such an amount that split hide or regenerated collagen fibers are completely immersed. The amount of the oxidant in this case is at least 1.0 equivalent, preferably at least 5.0 equivalent, and more preferably at least 10.0 equivalent based on the amount of methionine group. The concentration of the oxidant in solution thereof is at least 0.01 % by

weight, preferably at least 0.1 % by weight, more preferably at least 0.5 % by weight, and most preferably at least 0.8 % by weight. When the concentration of the oxidant is less than 0.01 % by weight, the reaction of the oxidant with methionine group is difficult, since the number of reactive sites is small. When the amount of the oxidant is less than 1.0 equivalent, the effect of deodorizing regenerated collagen fibers is insufficient. Usually, it is preferable that the temperature for the treatment is at most 35°C. The treatment is usually carried out for at least 5 minutes and the deodorizing effect is achieved in about 10 minutes in case of treating regenerated collagen fibers. On the other hand, the reaction is carried out thoroughly in case of treating split hide into which the oxidant does not permeate easily, with keeping split hide immersed in the oxidant solution overnight.

In case of treating a solubilized collagen aqueous solution, the amount of oxidant is at least 1.0 equivalent, preferably at least 5.0 equivalent, more preferably at least 10.0 equivalent. The concentration of the oxidant in the collagen aqueous solution is at least 0.01 % by weight, preferably at least 0.05 % by weight, more preferably at least 0.1 % by weight, and most preferably at least 0.2 % by weight. When the concentration of the oxidant is less than 0.01 % by weight, the reaction of oxidant with methionine group is difficult since the number of reactive sites is small. When the amount of the oxidant is less than 1.0 equivalent, the effect of deodorizing regenerated collagen fibers is insufficient. Preferably, the above treatment is carried out also at 35°C or lower. The solubilized collagen aqueous solution after adding the oxidant is mixed sufficiently for at least 30 minutes to contact the oxidant with collagen.

The regenerated collagen fibers of the present invention can be curled as aimed, other shapes being easily imparted thereto and setting being carried out with maintaining the shape properly, by thermally setting the regenerated collagen fibers by means of hot water
5 treatment at 20° to 100°C and heat drying treatment at 60° to 220°C. The detailed mechanism of the above shaping is still unknown. However, it is considered that hydrogen bond in regenerated collagen fibers is cut by the hot water treatment and the subsequent heat drying treatment enables re-bonding of hydrogen so that the re-bonded
10 structure corresponds to the aimed shape, making it possible to impart a reliable shape. The temperature of the treatment is a critical factor for the secure shaping.

The hot water treatment means a thermal treatment performed in the presence of water. The treatment may include
15 immersing fibers in water adjusted to a pre-determined temperature, or putting, into a plastic bag, fibers once immersed in water to contain sufficient water, sealing the bag and keeping the same in an air thermostat adjusted to a pre-determined temperature.

Specifically, a preferable treatment is such that regenerated
20 collagen fibers are fixed in a desirable shape (spiral shape and the like) with adjusting the temperature of the regenerated collagen fibers to 20° to 100°C in the presence of water. The temperature of the fiber is measured by inserting a thermocouple into the fiber bundle.

Though it is very difficult to determine the amount of water
25 existing on the surface of the regenerated collagen fibers in case of treating fibers in the presence of water, it is preferable to distribute water on the surface almost uniformly so that the regenerated collagen

fibers are treated equally.

According to this treatment conducted in the presence of water, it becomes difficult to impart a desirable shape to regenerated collagen fibers when the temperature of the regenerated collagen fibers is too low. On the other hand, it is feared that the regenerated collagen fibers are deformed when the temperature of the regenerated collagen fibers is too high. It is desired that the treatment is carried out at temperature of usually 20° to 100°C, preferably 50° to 100°C, more preferably 70° to 100°C, and most preferably 80° to 90°C.

The time for hot water treatment is suitably determined in accordance with atmosphere and temperature adopted for treating regenerated collagen fibers. The fibers are usually treated for at least 5 minutes, preferably at least 15 minutes.

Secondly, the heat drying treatment means a treatment to put a fiber bundle into a hot air convection dryer or to carry out heating by applying hot air to the fibers using a dryer and the like, while any conventional process may be used without particular limitation. Specifically, it is preferable to carry out drying under air of 60° to 220°C with fixing fibers in a pre-determined shape after the hot water treatment.

When the temperature is lower than 60°C, it becomes difficult to impart a desirable shape to the regenerated collagen fibers. On the other hand, when the temperature is higher than 220°C, it is feared that regenerated collagen fibers are deformed and colored. It is desired that the treatment is carried out at a temperature of usually 60° to 220°C, preferably 90° to 160°C, more preferably 100° to 130°C, and most preferably 110° to 120°C.

The time for heat drying treatment is suitably determined in accordance with temperature for drying, the amount of fibers to be dried and the like. The fibers are usually treated for at least 5 to 120 minutes, preferably at least 10 to 60 minutes, more preferably 15 to 30 minutes.

5 According to these treatments, regenerated collagen fibers can be set to desirable shapes with maintaining those shapes properly.

As a process for fixing regenerated collagen fibers in a desirable shape previously, there is a process to wind regenerated collagen fibers along a pipe or a bar, a process to stretch regenerated collagen fibers between two or more supporting points, a process to clip
10 regenerated collagen fibers between plates, and the like. Another process may be employed as long as the fibers are fixed in a desirable shape while water is supplied to the fibers sufficiently and the fibers can be dried at 60°C or more.

15 The regenerated collagen fibers of the present invention can be suitably used as fibers for hair and blankets, surgical thread, gut as well as fibers used for non-woven fabric, paper and the like.

Furthermore, since regenerated collagen fibers of the present invention are formed into a desirable shape easily with the shape being
20 maintained properly in addition to the advantages of light color and excellent touch in wet conditions, such regenerated collagen fibers are suitably used for curling hair ornaments such as wigs, hairpieces and doll hair or for shaping (setting) textile goods comprising woven fabrics or non-woven fabrics.

25 Hereinafter, the present invention is explained in more detail based on Examples, but the present invention is not limited thereto.

EXAMPLE 1

40018905-49494
FOXTET 50684004

A piece of cow split hide was subjected to solubilization treatment with alkali as a raw material, and 1,200 g of the treated skin (collagen content: 180 g) was dissolved in an aqueous solution containing lactic acid to prepare a concentrate solution adjusted to pH 3.5 and collagen concentration of 6 % by weight. The concentrate solution was subjected to stirring and defoaming under reduced pressure by using a stirring defoamer (type 8DMV made by DALTON Co. Ltd.). The solution was then transferred to a piston type concentrate solution tank for fiber spinning and kept under reduced pressure to carry out further defoming. The concentrate solution was extruded, supplied in fixed quantities by using a gear pump and then filtered through a sintered filter having a pore diameter of 10 μ m. The solution was discharged into a 25°C coagulation bath containing 20 % by weight of sodium sulfate (adjusted to pH 11 by boric acid and sodium hydroxide) through a spinning nozzle having a pore diameter of 0.30 mm, a pore length of 0.5 mm and a pore number of 300 at a spinning rate of 5 m/minute.

Then, the obtained regenerated collagen fibers were immersed into 16.6 kg of an aqueous solution containing 1.7 % by weight of epichlorohydrin, 0.9 % by weight of 2,4,6-tris(dimethylaminomethyl)phenol, 0.09 % by weight of salicylic acid and 13 % by weight of sodium sulfate at 25°C for 24 hours. The amount of added epichlorohydrin was 42.6 equivalent based on the amount of amino group in collagen.

After an hour of washing by running water, the fibers were immersed in 16.6 kg of an aqueous solution containing 10 % by weight

of basic aluminum chloride (Bellcotan AC-P available from Nippon Fine Chemical Co., Ltd.) and 5 % by weight of sodium chloride at 25°C for 12 hours. Thereafter, the obtained fibers were washed by running water for two hours.

5 Then, an oiling agent containing emulsion of silicones modified with amino group and a PLURONIC polyether antistatic agent was applied to the fibers by immersing part of the fibers in a bath filled with the oiling agent. In a hot air convection dryer (PV-221 made by Tabai Espec Corporation) adjusted to 50°C, one end of a fiber bundle
10 was fixed, and a weight of 3.6 g was attached to each fiber at the other end of the bundle. Drying was carried out for two hours in the state of tension and measurement was conducted.

EXAMPLE 2

15 Experiment was carried out in the same manner as in Example 1 except for changing the monofunctional epoxy compound to phenyl glycidyl ether.

EXAMPLE 3

20 Experiment was carried out in the same manner as in Example 1 except for changing the amount of basic aluminum chloride to 5 % by weight.

EXAMPLE 4

25 Experiment was carried out in the same manner as in Example 2 except for changing the amount of basic aluminum chloride to 5 % by weight.

EXAMPLE 5

Experiment was carried out in the same manner as in Example 1 except that the treatment with aluminum salt was carried out by immersing fibers in 16.6 kg of an aqueous solution containing 5 % by weight of basic aluminum chloride, 6 % by weight of sodium chloride and 1 % by weight of sodium formate at 4°C for 12 hours.

EXAMPLE 6

The regenerated collagen fibers obtained in the same manner as in Example 1 were immersed in 16.5 kg of an aqueous solution containing 1.7 % by weight of epichlorohydrin, 0.09 % by weight of 2,4,6-tris(dimethylaminomethyl)phenol, 0.009 % by weight of salicylic acid and 13 % by weight of sodium sulfate at 25°C for 24 hours. The amount of added epichlorohydrin was 42.1 equivalent based on the amount of amino group in collagen.

After an hour of washing by running water, the fibers were immersed in 16.5 kg of an aqueous solution containing 6 % by weight of basic aluminum chloride and 5 % by weight of sodium chloride at 30°C for 12 hours. Thereafter, the obtained fibers were washed by running water for two hours.

Then, an oiling agent containing emulsion of silicones modified with amino group and a PLURONIC polyether antistatic agent was applied to the fibers by immersing part of the fibers in a bath filled with the oiling agent. In a hot air convector dryer adjusted to 50°C, one end of a fiber bundle was fixed, and a weight of 3.6 g was attached to each fiber at the other end of the bundle. Drying was carried out for two hours in the state of tension and measurement was conducted.

EXAMPLE 7

Experiment was carried out in the same manner as in Example 6 except that 110 g of a hydrogen peroxide aqueous solution diluted to a concentration of 10 % by weight (the amount of hydrogen peroxide is 30 equivalent based on methionine group) was added to the concentrate solution before defoaming, and then the mixture was stirred for 30 minutes by using a kneader (type PNV-5 made by Irie Shokai Co., Ltd.) and kept overnight.

EXAMPLE 8

Experiment was carried out in the same manner as in Example 7 except that the treatment with aluminum salt was carried out by immersing fibers in 16.5 kg of an aqueous solution containing 5 % by weight of basic aluminum chloride, 6 % by weight of sodium chloride and 1 % by weight of sodium formate at 4°C for 15 hours.

EXAMPLE 9

Experiment was carried out in the same manner as in Example 7 except for changing the monofunctional epoxy compound to phenyl glycidyl ether.

EXAMPLE 10

Experiment was carried out in the same manner as in Example 8 except for changing the time for immersion in an aqueous solution of basic aluminum chloride (prepared in the same manner as in Example 8) to 10 minutes.

EXAMPLE 11

Experiment was carried out in the same manner as in Example 7 except that the treatment with aluminum salt was carried out by immersing fibers in 16.5 kg of an aqueous solution containing 5 % by weight of aluminum sulfate 13 to 14 hydrate (crystal) (available from
5 NACALAI TESQUE, INC.), 1 % by weight of trisodium citrate dihydrate and 1.3 % by weight of sodium hydroxide at 30°C for 15 hours.

EXAMPLE 12

10 Experiment was carried out in the same manner as in Example 11 except for changing the time for immersion in an aqueous solution of aluminum sulfate(prepared in the same manner as in Example 11) to 10 minutes.

EXAMPLE 13

15 Experiment was carried out in the same manner as in Example 7 except that oxidation was carried out by immersing fibers in 1,836 g of an aqueous solution containing 2.0 % by weight of hydrogen peroxide (the amount of hydrogen peroxide is 100 equivalent based on
20 methionine group) and then the mixture was kept overnight.

EXAMPLE 14

Experiment was carried out in the same manner as in Example 6 except that the obtained regenerated collagen fibers were
25 immersed in 16.5 kg of an aqueous solution containing 1.0 % by weight of hydrogen peroxide and 13 % by weight of sodium sulfate at 25°C for an hour after fiber spinning.

COMPARATIVE EXAMPLE 1

Experiment was carried out in the same manner as in Example 8 except that insolubilization treatment was carried out by immersing the regenerated collagen fibers in an aqueous solution of 25°C containing 15 % by weight of sodium sulfate and 0.5 % by weight of formaldehyde (adjusted to pH 9 by using boric acid and sodium hydroxide) for 15 minutes instead of the treatment with epichlorohydrin.

COMPARATIVE EXAMPLE 2

Experiment was carried out in the same manner as in Example 7 except that the treatment with aluminum salt was omitted.

The thus-obtained regenerated collagen fibers were examined with regard to denier, aluminum content, hair iron heat resistance, forming of curl, curling characteristics, generation of foul odor and gas component in the gas phase according to the following method.

(Denier)

Denier was measured in an atmosphere adjusted to temperature of $20 \pm 2^\circ\text{C}$ and relative humidity of $65 \pm 2\%$ by using a denier measurement Denier Computer DC-77A (made by Search Co., Ltd.).

(Aluminum content)

After drying the regenerated collagen fibers in a desiccator, 0.1 g of the fibers were heated and dissolved in a solution obtained by mixing 5 ml of nitric acid and 15 ml of hydrochloric acid. The mixture was cooled and diluted fiftyfold with water to measure the aluminum content in the diluted aqueous solution by using an atomic absorption

measurement equipment (Z-5300 type) made by Hitachi, Ltd. The aluminum content measured according to this method means the content of metal aluminum alone. The value was multiplied by 1.89 to calculate the content of aluminum oxide (Al_2O_3).

5 (Hair iron heat resistance)

The following procedures were taken in an atmosphere adjusted to temperature of $20 \pm 2^\circ\text{C}$ and relative humidity of $65 \pm 2\%$.

Fibers were opened sufficiently and put together into a bundle of 22,000 dtex and 250 mm long. A hair iron (Perming Iron made by Hakko Kogyo Co., Ltd.) was pressed lightly to the bundle with adjusting temperature to various values. By a quick slide of the iron both on the top face and the bottom face of the bundle (two seconds/slide), water on the fiber surface was vaporized. The fiber bundle was nipped with the iron, which was slid from the root to the tip in five seconds. After the treatment, shrinkage percentage of the bundle was determined and crimple of the fiber tip was examined. The shrinkage percentage was calculated by using L indicating fiber length before ironing and L_0 indicating fiber length after ironing (in case where the bundle is twisted, L_0 was measured by extending the twisted bundle) according to the following equation (1):

$$\text{Shrinkage percentage} = [(L - L_0)/L] \times 100 \quad (1)$$

The maximum temperature at which the shrinkage percentage after ironing was at most 5 % and crimple of the fibers was not observed was described as the temperature for hair iron heat resistance. The temperatures of the hair iron were set in 10°C increments. A new fiber bundle without prior ironing was used at every measurement at each temperature.

(Forming of curl and measurement of curling characteristics)

Forming of curl and measurement of curling characteristics were carried out in the following manner.

- 5 (1) A fiber bundle opened sufficiently and adjusted to 145,000 dtex (6.5 g/45 cm) was folded into two and tied with string. The bundle was trimmed off in the same fiber length at the point 20 cm from the knot.
- (2) The fiber bundle was divided into eight portions. Each portion was wound around an aluminum pipe having a major diameter of 12 mm and both ends of the bundle was fixed to the pipe by rubber bands to
10 prevent the bundle from moving.
- (3) The fiber-wound rod was then put into hot water adjusted to 85°C for 15 minutes to moisturize the fibers.
- (4) The rod was taken from hot water and dried in a hot air convection dryer (PV-221 made by Tabai Espec Corporation) for 15 minutes.
- 15 (5) Then, the rod was took out from the hot air convection dryer and cooled at room temperature for about 15 minutes to unwind the fiber bundle.
- (6) As plain shampoo, the fiber bundle was washed by shaking 20 times in hot water of 40°C. The fiber bundle was taken out from hot water,
20 and water on the surface was first wiped off by a towel and then removed by shaking. The bundle was hung up with keeping the spiral form, and curl length from the knot to the curl tip (C_p cm) without load and the length in case of stretching the curl (L_p cm) were measured, respectively. The bundle was then dried in the hot air convection dryer adjusted to
25 50°C.
- (7) The dried fiber bundle was shampooed with combing 20 times in hot water adjusted to 40°C, containing 0.2 % of shampoo (Super Mild

Shampoo/ Floral Fruity available from Shiseido Co. Ltd.). Light rinsing was carried out with rubbing under hot running water of 40°C. Water was removed in the same manner as in (6). Thereafter, the bundle was hung up with keeping the spiral form, and curl length from the knot to the curl tip (C_s cm) without load and the length in case of stretching the curl (L_s cm) were measured, respectively. The bundle was then dried again in the hot air convection dryer adjusted to 50°C.

(8) The procedure in (7) was repeated to evaluate shampoo resistance of the curl (curling percentage against the number of shampoo)

- 10 (9) Curling characteristics for evaluation were calculated in accordance with the following equations (2), (3) and (4).

Curling percentage immediately after plain shampoo (P_s)

$$P_s = (20 - C_p) \times 100 / L_p (\%) \quad (2)$$

Curling percentage immediately after shampoo (Sc)

15
$$Sc = (20 - C_s) \times 100 / L_s (\%) \quad (3)$$

Curling retention immediately after shampoo (Ss)

$$Ss = (L_s - C_s) \times 100 / (L_s - C_p) (\%) \quad (4)$$

Table 1 and Table 2 show curling percentage after plain shampoo, curling percentage immediately after five shampoos and curling retention immediately after five shampoos as representative values.

(Confirmation of odor)

In consideration of heat treatment for regenerated collagen fibers by dryer or the like, fibers were subjected to thermal treatment for 10 minutes in a hot air convection dryer adjusted to 100°C. Sniffing of the fibers was carried out to confirm whether typical odor of a sulfur-containing compound was generated or not.

(Gas component analysis in gas phase)

The fiber sample thermally treated at 100°C was placed in a 20 ml vial bottle in an amount of 0.2 g. The sample was re-heated at 60°C for 10 minutes, and the gas phase was analyzed with measuring amounts of ions detected by gas chromatography mass spectrometer QP-5050 made by Shimadzu Corporation with increasing temperature at a rate of 10°C/minute between 40° to 200°C and at a rate of 20°C/minute between 200° to 280°C.

10

TABLE 1

Ex. No.	Denier (d)	Aluminum oxide content (%)	Curling percentage after plain Shampoo (%)	Curling percentage immediately after five shampoos (%)	Curling retention immediately after five shampoos (%)
1	67	12.5	28.2	20.5	70.0
2	78	11.5	23.1	15.9	65.0
3	61	10.5	28.2	19.5	66.0
4	75	9.5	22.6	15.4	64.1
5	65	11.2	28.3	19.7	67.1

TABLE 2

Ex. No.	Denier (dtex)	Aluminum oxide content (%)	Curling percentage after plain shampoo (%)	Curling percentage immediately after five shampoos (%)	Curling retention immediately after five shampoos (%)	Hair iron heat resistance (°C)	Generation of foul odor
6	66	8.2	28.2	19.5	66.0	140	generated
7	67	8.5	28.2	19.5	66.0	140	none
8	71	11.2	28.3	19.7	67.1	160	none
9	83	11.5	23.1	15.9	65.0	-	none
10	61	4.7	23.1	15.4	62.5	130	none
11	72	11.7	25.6	15.4	55.6	150	none
12	58	4.3	21.5	12.8	54.1	130	none
13	68	8.5	28.4	19.6	65.5	140	none
14	66	8.4	28.3	19.5	65.7	140	none
Com. Ex. 1	70	13.0	23.1	5.1	12.2	160	none
Com. Ex. 2	54	0	12.5	7.5	50.0	120	none

denier: 1 dtex (decitex) = 0.9 d (denier)

The results in Table 1 and Table 2 show that it is possible to obtain fibers which has light color and excellent wet touch by treating regenerated collagen fibers with a monofunctional epoxy compound and aluminum salt. The results also show that it is possible to obtain fibers
5 which can be formed into desirable shapes by keeping fibers at temperature of 20° to 100°C in the presence of water and then drying fibers at temperature of 60° to 220°C. In addition, it was also possible to obtain fibers which did not give off foul odor typical to a sulfur-containing compound even at heating by treating collagen with an
10 oxidant before the treatment with the monofunctional epoxy compound.

The results of the gas component analysis are shown in Fig. 1 and Fig. 2.

Fig. 1 shows the results of analysis of gas generated from the fibers prepared in Example 6. Four peaks were detected in this
15 measurement. It was revealed that peak 1 represented methyl mercaptan, peak 2 dimethyl sulfide, peak 3 dimethyl disulfide and peak 4 3-(methylthio)-propion aldehyde as a result of analysis of the four peaks by mass spectrography.

Fig. 2 shows the results of analysis of gas generated from the
20 fibers prepared in Example 7. No peak was observed in this measurement.

These results show that generation of foul odor typical to a sulfur-containing compound can be inhibited in case of using regenerated collagen fibers obtained by reacting a monofunctional epoxy
25 compound with collagen after treatment with an oxidant.

INDUSTRIAL APPLICABILITY

The regenerated collagen fibers of the present invention have light color and excellent wet touch. In addition, generation of foul odor typical to a sulfur-containing compound at thermal treatment can be
5 inhibited by reacting a monofunctional epoxy compound with collagen after treating methionine group in collagen with an oxidant.

At the same time, the regenerated collagen fibers of the present invention can be formed into desirable shapes easily with the shape being maintained properly, and suitably used for curling hair
10 ornaments such as wigs, hairpieces and doll hair or for shaping (setting) textile goods comprising woven fabrics or non-woven fabrics.

10048905-121701

CLAIMS

1. A regenerated collagen fiber which is obtained by treating collagen with a monofunctional epoxy compound and an aluminum salt.

5

2. The regenerated collagen fiber of Claim 1, wherein said monofunctional epoxy compound is a compound represented by the following formula (I):

10



in which R indicates a substituent group represented by R_1- , $\text{R}_2-\text{O}-\text{CH}_2-$ or $\text{R}_2-\text{COO}-\text{CH}_2-$, R_1 in said substituent group indicates a hydrocarbon group having at least 2 carbon atoms or CH_2Cl and R_2 indicates a hydrocarbon group having at least 4 carbon atoms.

15

3. The regenerated collagen fiber of Claim 2, wherein said R_1 in the formula (I) indicates a hydrocarbon group having 2 to 6 carbon atoms or $-\text{CH}_2\text{Cl}$ and R_2 indicates a hydrocarbon group having 4 to 6 carbon atoms.

20

4. The regenerated collagen fiber of Claim 1, 2 or 3, wherein a methionine group in said collagen is a sulfoxidized methionine group or a sulfonated methionine group.

25

5. A process for preparing the regenerated collagen fiber of

Claim 1 which comprises treating collagen with a monofunctional epoxy compound, and then treating the same in such a way that 2 to 40 % by weight of an aluminum salt converted to an aluminum oxide basis is contained to said collagen.

5

6. The process for preparing a regenerated collagen fiber of Claim 5, wherein said collagen is treated with an oxidant and then treated with the monofunctional epoxy compound and the aluminum salt.

10

7. The process for preparing a regenerated collagen fiber of Claim 6, wherein said oxidant is hydrogen peroxide.

8. A process for setting a regenerated collagen fiber which comprises thermally setting the regenerated collagen fiber of Claim 1, 2 or 3 by means of hot water treatment at 20° to 100°C and heat drying treatment at 60° to 220°C.

15

FIG. 1





FIG. 2



DECLARATION FOR PATENT APPLICATION

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled REGENERATED COLLAGEN FIBER REDUCED IN ODOR AND IMPROVED IN SUITABILITY FOR SETTING, PROCESS FOR PRODUCING THE SAME, AND METHOD OF SETTING, the specification of which:

- ☒ is attached hereto.
- ☒ was filed on June 23, 2000 as PCT International Application Serial No. PCT/JP00/04126.
- ☐ and was amended on _____ (if applicable).

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the patentability as defined in Title 37, Code of Federal Regulations, § 1.56(a).

I hereby claim foreign priority benefits under 35 U.S.C. § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s)Priority Claimed

<u>179328/1999</u>	<u>Japan</u>	<u>25/6/1999</u>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
(Number)	(Country)	(Day/Month/Year Filed)	Yes	No
<u>191859/1999</u>	<u>Japan</u>	<u>6/7/1999</u>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
(Number)	(Country)	(Day/Month/Year Filed)	Yes	No

I hereby claim the benefit under 35 U.S.C. § 119(e) of any United States provisional application(s) listed below:

_____ (Application Serial No.)	_____ (Filing Date)
-----------------------------------	------------------------

I hereby claim the benefit under 35 U.S.C. § 120 of any United States application(s), or § 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. § 112, I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR § 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application:

_____ (Application Serial No.)	_____ (Filing Date)	_____ (Status-patented, pending, abandoned)
-----------------------------------	------------------------	--

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Inventor's Signature

Full name of sole or first inventor

Residence

Citizenship

Post Office Address

Masahiro Ueda Date: 7/12/2001
Masahiro UEDA
Himeji-shi, HYOGO 670-0081 JAPAN
Japanese
1-3-28, Taderahigashi, Himeji-shi, HYOGO 670-0081 JAPAN

BRINKS HOFER GILSON & LIONE

P.O. Box 10395

Chicago, IL 60610

(312) 321-4200



00757

PATENT TRADEMARK OFFICE

Case No.

240 Inventor's Signature

Full name of second joint inventor, if any

Residence

Citizenship

Post Office Address

Yoshihiro MAKIHARA

Date: 7/12/2001

Yoshihiro MAKIHARA

Takasago-shi, HYOGO 676-0026 JAPAN

Japanese

Kounryo, 2-63, Takasago-cho Okihama-cho, Takasago-shi, HYOGO 676-0026 JAPAN

Inventor's Signature

Full name of third joint inventor

Residence

Citizenship

Post Office Address

Takashi Ueda

Date: 7/12/2001

Takashi UEDA

Amagasaki-shi, HYOGO 661-0975 JAPAN

Japanese

4-2-27, Shimosakabe, Amagasaki-shi, HYOGO 661-0975 JAPAN

Inventor's Signature

Full name of fourth joint inventor

Residence

Citizenship

Post Office Address

Kunihiko MATSUMURA

Date: 7/12/2001

Kunihiko MATSUMURA

Kobe-shi, HYOGO 655-0872 JAPAN

Japanese

Sanseiso 1104, 6-31-17, Shioya-cho, Tarumi-ku, Kobe-shi, HYOGO 655-0872 JAPAN

Inventor's Signature

Full name of fifth joint inventor

Residence

Citizenship

Post Office Address

Date:

Inventor's Signature

Full name of sixth joint inventor

Residence

Citizenship

Post Office Address

Date:

Inventor's Signature

Full name of seventh joint inventor

Residence

Citizenship

Post Office Address

Date:

rev. Dec.-99

Document2

Inventor(s): Masahiro UEDA, Yoshihiro MAKIHARA, Takashi UEDA and Kunihiro MATSUMURA
 Title: REGENERATED COLLAGEN FIBER REDUCED IN ODOR AND IMPROVED IN SUITABILITY FOR SETTING, PROCESS FOR PRODUCING THE SAME, AND METHOD OF SETTING

POWER OF ATTORNEY

The specification of the above-identified patent application:

- ☒ is attached hereto
☒ was filed on June 23, 2000 as PCT International Application Serial No. PCT/JP00/04126

I hereby revoke all previously granted powers of attorney in the above-identified patent application and appoint the following attorneys to prosecute said patent application and to transact all business in the Patent and Trademark Office connected therewith:

Richard G. Lione - 19,795

Please address all correspondence and telephone calls to Richard G. Lione in care of:

Brinks Hofer Gilson & Lione
 P.O. Box 10395
 Chicago, IL 60610
 (312)321-4200

The undersigned hereby authorizes the U.S. attorneys named herein to accept and follow instructions from Richard G. Lione as to any action to be taken in the Patent and Trademark Office regarding this application without direct communication between the U.S. attorney and the undersigned. In the event of a change in the persons from whom instructions may be taken, the U.S. attorneys named herein will be so notified by the undersigned.

KANEKA CORPORATION, a corporation, certifies that it is the assignee of the entire right, title and interest in the patent application identified above by virtue of either:

☒ An assignment from the inventor(s) of the patent application identified above, a copy of which is attached hereto.
 OR

An assignment from the inventor(s) of the patent application identified above. The assignment was recorded in the Patent and Trademark Office at Reel _____, frame _____.
 OR

A chain of title from the inventor(s), of the patent application identified above, to the current assignee as shown below:

1. From _____ To: _____
 The document was recorded in the Patent and Trademark Office at Reel _____, frame _____, or a copy thereof is attached.
2. From _____ To: _____
 The document was recorded in the Patent and Trademark Office at Reel _____, frame _____, or a copy thereof is attached.

☐ Additional documents in the chain of title are listed on a supplemental sheet.

The undersigned has reviewed the assignment or all the documents in the chain of title of the patent application identified above and, to the best of undersigned's knowledge and belief, title is in the assignee identified above.

The undersigned (whose title is supplied below) is empowered to act on behalf of the assignee.

I hereby declare that all statements made herein of my own knowledge are true, and that all statements made on information and belief are believed to be true; and further, that these statements are made with the knowledge that willful false statements, and the like so made, are punishable by fine or imprisonment, or both, under Section 1001, Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

Signature: Tatehiko Nishida Date: Dec. 7, 2001
 Name: Tatehiko Nishida
 Title: General Manager, Patent Department

Inventor(s): Masahiro UEDA, Yoshihiro MAKIHARA, Takashi UEDA and Kunihiko MATSUMURA
 Title: REGENERATED COLLAGEN FIBER REDUCED IN ODOR AND IMPROVED IN SUITABILITY FOR SETTING, PROCESS FOR PRODUCING THE SAME, AND METHOD OF SETTING

POWER OF ATTORNEY

The specification of the above-identified patent application:

- ☒ is attached hereto
☒ was filed on June 23, 2000 as PCT International Application Serial No. PCT/JP00/04126

I hereby revoke all previously granted powers of attorney in the above-identified patent application and appoint the following attorneys to prosecute said patent application and to transact all business in the Patent and Trademark Office connected therewith:

Richard G. Lione - 19,795

Please address all correspondence and telephone calls to Richard G. Lione in care of:

Brinks Hofer Gilson & Lione
 P.O. Box 10395
 Chicago, IL 60610
 (312)321-4200

The undersigned hereby authorizes the U.S. attorneys named herein to accept and follow instructions from Richard G. Lione to any action to be taken in the Patent and Trademark Office regarding this application without direct communication between the U.S. attorney and the undersigned. In the event of a change in the persons from whom instructions may be taken, the U.S. attorneys named herein will be so notified by the undersigned.

HOKUYO CO., LTD., a corporation, certifies that it is the assignee of the entire right, title and interest in the patent application identified above by virtue of either:

☒ An assignment from the inventor(s) of the patent application identified above, a copy of which is attached hereto.
 OR

☐ An assignment from the inventor(s) of the patent application identified above. The assignment was recorded in the Patent and Trademark Office at Reel _____, frame _____.
 OR

A chain of title from the inventor(s), of the patent application identified above, to the current assignee as shown below:

1. From _____ To: _____
 The document was recorded in the Patent and Trademark Office at Reel _____, frame _____, or a copy thereof is attached.
2. From _____ To: _____
 The document was recorded in the Patent and Trademark Office at Reel _____, frame _____, or a copy thereof is attached.

☐ Additional documents in the chain of title are listed on a supplemental sheet.

The undersigned has reviewed the assignment or all the documents in the chain of title of the patent application identified above and, to the best of undersigned's knowledge and belief, title is in the assignee identified above.

The undersigned (whose title is supplied below) is empowered to act on behalf of the assignee.

I hereby declare that all statements made herein of my own knowledge are true, and that all statements made on information and belief are believed to be true; and further, that these statements are made with the knowledge that willful false statements, and the like so made, are punishable by fine or imprisonment, or both, under Section 1001, Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

Signature: Fujio Matsumura Date: Dec. 6, 2001
 Name: Fujio Matsumura
 Title: President